



DE-B311 DIELECTRIC

PRODUCT DATA SHEET




SUITABLE SUBSTRATES

Properly prepped, primed, and OEM grade clear coat to include but not limited to:

- Plastic - Metal -Carbon Fiber
- Wood - Fiberglass

**Conductive substrates must be fully encapsulated so substrate will not get energized



MIXING

- Contents premixed and ready to use.
- Thoroughly hand shake before use.
- Use ONLY glass or plastic stirrer if needed
- Strain with nylon 120 mesh or 125 microns filter





Premixed




APPLICATION

- Apply 2 wet cross coats.
- 50 to 75% overlap
- 20 – 25 psi at nozzle for HVLP
- Constantly agitate material



DRY SCHEDULE

- 5 – 10 minutes flash between coats
- Allow 15 – 30 minutes between each layer
- No longer than 24 hours between layers or recoat
- @ 70 F / 30% humidity



NOTES

Pour remainder material back in original canister after thoroughly agitated

Shelf life: 6 months

Approximate Coverage: 4oz/118mL = 1-2 square feet

8oz/237mL = 3-4 square feet



PERSONAL PROTECTION

- For use by trained professionals only.
- Read all labels, directions, and SDS before use
- Use all appropriate Personal Protective Equipment while mixing and spraying